

TIF700HP Series thermally conductive interface materials are applied to fill the air gaps between the heating elements and the heat dissipation fins or the metal base. Their flexibility and elasticity make them suited to coat very uneven surfaces. Heat can transmit to the metal housing or dissipation plate from the heating elements or even the entire PCB, which effectively enhances the efficiency and life-time of the heat-generating electronic components.

Features


- » Good thermal conductivity: 7.5W/mK
- » Naturally tacky needing no further adhesive coating
- » Soft and Compressible for low stress applications
- » Available in varies thickness

Application

- » Cooling components to the chassis of frame
- » Set Top Box
- » Car Battery & Power Supply
- » Charging Pile
- » LED TV/ Lighting
- » Graphics Card Thermal Module

Typical Properties of TIF700HP Series		
Color	Gray	Visual
Construction	Ceramic filled silicone elastomer	*****
Thickness range	0.030"-0.400"	ASTM D374
Specific Gravity	3.5 g/cc	ASTM D297
Operating Temp	-40 ~160 °C	*****
Dielectric Breakdown Voltage	5.5 KV	ASTM D149
Dielectric Constant@1MHz	4.5 MHz	ASTM D150
Volume Resistivity	5.2X10 ¹³ Ohm-meter	ASTM D257
Thermal Conductivity	7.5 W/mK	ASTM D5470
	7.5 W/mK	GB-T32064
Outgassing (TML)	0.30%	ASTM E595
Flame Rating	UL94 V0	UL E331100

Psi. vs. Thermal Resistance



Product Specification

Product Thicknesses


0.030-inch to 0.400-inch (0.75mm to 10.0mm)

Product Sizes

10" x 16"(254mm x406mm)

Individual die cut shapes and custom thickness can be supplied. Please contact us for confirming.

Product Identification:



Thermally Conductive Materials

Heat Generating Materials

Thermally Conductive Plastics

Foaming Silica Gel

Die-Cutting Products

Canada:

Tel: +001-604-2998559
E-mail: sales@thermazig.com

China:

Tel: +86-769-38801208
E-mail: jor@ziitek.com

Taiwan:

Tel: +886-2-22771007
E-mail: frances@ziitek.com.tw

Thermal Conductive Interface Materials
Application Technology Download



The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.

http://www.ziitek.com